

Afrisol Range of White Metals

Metal Composition (% metal by weight)									
Alloy No	Brinell Hardness	Sn	Sb	Cu	Ag	Bi	Cd	Pb	Pouring Temp.
WM 90	26.5	90.0	7.0	3.0	-	-	-	-	340-370
WM 84	31.0	84.0	10.0	6.0	-	-	-	-	410-460
WM 80	30.5	80.0	9.0	6.0	-	-	-	5.0	410-460
WM 72	27.0	72.0	10.0	6.0	-	-	-	12.0	410-450
WM 40	24.2	40.0	15.0	3.0	-	-	-	42.0	350-400
WM 30	24.0	30.0	16.0	1.0	-	-	-	53.0	350-400
WM 15	24.0	15.0	14.0	0.5	-	-	-	70.5	330-360
WM 06	24.0	6.0	14.0	-	-	-	-	80.0	320-340
WM 11R		90	7.5	3.0	-	-	-	-	
WM 175		75.0	14.5	7.5	-	-	-	3.0	